

















## Altro Transflor Tungsten™

Colours Colores Farben	6		
Flooring Type Tipo de pavimento Belagsart		EN14565	Safety flooring Suelo de seguridad antideslizante Sicherheitsbodenbelag
Classification for use Areas de uso Einsatzbereiche		EN 685	34 & 43 34 y 43 34 & 43
Slip Resistance Resistencia al deslizamiento Rutschsicherheit		TRRL DIN 51130 EN13845 EN 13893 BAM ASTM D2047	≥ 40 R11 ESf DS Extremely slip resistant ≥ 0.6
Thickness Espesor total Gesamtdicke		EN 428	2.0mm 0.08"
Wear Layer Capa de uso Nutzschicht		EN 429	1.0mm 0.04"
Flexibility Flexibilidad Flexibilität		EN 435	Pass Conforme geeignet
Weight Peso Flächengewicht		EN 430	2.7kg/m <sup>2</sup> 4.98lbs/ycd <sup>2</sup>
Roll Dimensions Dimensiones del rollo Rollenabmessungen		EN 426	2m x 20m - 40m <sup>2</sup> 6.58' x 65.62'
Light Fastness Resistencia a la luz Lichtechtheit		EN 20105-B02	≥6
Sound Insulation Aislamiento acústico Trittschall		ISO 140-8	1dB
Wear Resistance Abrasión Verschleißverhalten		EN13845 Annex D	≤10% Particles lost over 50,000 cycles ≤10% de las partículas perdidas en 50,000 ciclos ≤10% Partikelverlust bei 50.000 Umdrehungen
Indentation Punzonamiento Resteindruck		EN 433	≤ 0.1mm ≤ 0.004"
Fire Performance Reacción al fuego Brandverhalten		BS 6853 EN 45545 DIN 5510 ASTM E648 ASTM E662  BSS 7238 BSS 7239 EN13501	Category 1a HL2 SF3 FED ≤1 Class 1 / Clase 1 / Klasse 1 Ds @ 1.5min <100 Ds @ 4min <200 Pass US Requirements Pass US Requirements Class Bfl s1
Chemical Resistance* Resistencia a los productos químicos Chemikalieneinwirkung		EN 423	Good Buena beständig
Castor Chair Abrasion Huellas de sillas de ruedas Stuhlrollenbeanspruchung		EN 425	Pass Conforme geeignet
Dimensional Stability Estabilidad dimensional Formstabilität		EN 434	≤0.4%