

# Altro Whiterock™ hygienic wall and ceiling systems

JULY 2011



Data sheet

'EU' grade - extruded W160/161,  
Altro Whiterock Chameleon™

A high gloss, solid colour sheet for areas requiring a decorative appearance. Also suitable where sheet may come into contact with food.

## Description

Extruded semi-rigid PVCu sheet.

Colour:	11 colours
Surface finish:	Gloss
Thickness:	2.5mm
Size:	2500 x 1220mm 3000 x 1220mm
Weight:	3.5kg per m <sup>2</sup>
Maximum service temp:	60°C

Altro Chameleon W160/161 PVCu extruded sheet is supplied with a protective film on its face, which can be left in place until the room, is ready for use. This also helps to protect the surface from dust while other trades are in the area. It is ideal for applications requiring a hygienic easy-to-clean, almost maintenance free wall finish, which conforms to UK hygiene requirements.

## Fixing

The sheets can be fixed directly to most dry substrates depending on its surface suitability, using one of the following methods:

1. AltroFix™ W139 all over adhesive
2. AltroFix™ W157 all over adhesive

## Cutting

A jigsaw is the best method, however a fine toothed hand saw or circular saw with pressure guide can also be used.

## Jointing

- see relevant detailed drawings

1. A high impact colour co-ordinating extruded PVCu 'H' joint trim (available in two part or single part profiles), incorporating a watertight seal at the mouth of the joint, which is unique to Altro Whiterock.
2. Hot welded - ask for details.

## Internal/external corners

Altro Whiterock Chameleon is normally thermoformed on site, so that window and door reveals are neatly clad without an edge joint. However, profiles are available for the self-installer to cope with these details.

## Cleaning

Regular cleaning using a soft cloth and a suitably diluted mild detergent is all that is normally required.

**Do not use abrasive pads or wire wool.**

**Do not clean above 60°C.**

**Cleaning cards are available on request.**

## Chemical resistance

Resistant to a wide range of chemicals, specific details on request.

## Availability

Ex-stock.

## Storage & conditioning (on-site)

Sheets should be stored flat, fully supported and left for 24 hours to attain the ambient room temperature prior to installation (min 14°C).

## Limitations of use

Altro Whiterock Chameleon W160/161 has a maximum working temperature of 60°C. For temperatures above this use stainless steel. Stainless steel must be used for all open flame areas (available cut to size). If a layout showing the position of equipment can be supplied, we will provide specific advice as to the best combination of materials to use

## Typical applications

- Receptions/leisure/retail areas
- Canteens/serveries/vending areas
- Recovery/wards/intensive care areas
- Doctors/dentists/veterinary practices
- Shower/toilet/changing room areas
- Corridors/classrooms/swimming pools

Our Technical Services Department is available for advice on 01462 707600.

## Technical data

Property	DIN	Values
Density (g/cm <sup>3</sup> )	53479	1.38
Modulus of elasticity (Mpa)	53455	3200
Yield point street (Mpa)	53455	70
Impact resistance Charpy at 20°C with U notched sample (Kj/m <sup>2</sup> )	53453	2.15
Vicat point at 5kg (°C)	53460	72
Coefficient of thermal expansion (10 <sup>4</sup> /K)	53328	0.00007
Maximum service temperature (°C)		60
Thermal Conductivity (W/mK)	52612	0.16
Hardness Shore D	53505	77
Steel ball impact sample of 80x80 on a hole of 50mm diameter (Joule)		12
Light transmission (%)	ASTM D 1003	87+/-1.5
Haze (%)	ASTM D 1003	1+/-0.50
Light reflectance values (LRV)	D65 artificial daylight	26-77 (ask for details)
Flammability		
Surface spread of flame	BS 476 Part 7 1987	Class 1
Fire propagation	BS 476 Part 6 1989	Class 0*

(\*when fixed to a non-combustible substrate)

Subject to change without notice.

for further information or technical advice

tel: 01462 707600 fax: 01462 707504

e-mail: [enquiries@altro.com](mailto:enquiries@altro.com) or explore [www.altro.com](http://www.altro.com)